

White Membrane

Solar Reflectance: 0.87
Thermal Emittance: 0.88

SRI Value – Low Wind: 108.9
SRI Value – Medium Wind: 109.0
SRI Value – High Wind: 109.1

Tan Membrane

Solar Reflectance: 0.366
Thermal Emittance: 0.87

SRI Value – Low Wind: 39.1
SRI Value – Medium Wind: 39.9
SRI Value – High Wind: 40.7

Gray Membrane

Solar Reflectance: 0.163
Thermal Emittance: 0.88

SRI Value – Low Wind: 12.4
SRI Value – Medium Wind: 13.5
SRI Value – High Wind: 14.5

Red Membrane

Solar Reflectance: 0.243
Thermal Emittance: 0.88

SRI Value – Low Wind: 22.8
SRI Value – Medium Wind: 23.8
SRI Value – High Wind: 24.7

Brown Membrane

Solar Reflectance: 0.079
Thermal Emittance: 0.87

SRI Value – Low Wind: 0.8
SRI Value – Medium Wind: 2.3
SRI Value – High Wind: 3.6

Evergreen Membrane

Solar Reflectance: 0.073
Thermal Emittance: 0.88

SRI Value – Low Wind: 0.9
SRI Value – Medium Wind: 2.1
SRI Value – High Wind: 3.2